

3M CERAMIC IR SERIES
Total Solar Energy Rejected
VLT
UV Block
IRR*
IRER**
Glare Reduction

IR 15	IR 25	IR 30	IR 35
59%	57%	55%	52%
19%	30%	37%	45%
99%	99%	99%	99%
90%	90%	88%	85%
61%	63%	62%	61%
70%	65%	57%	49%

Performance data generated using applicable industry test methods and standards.

*Infrared rejection measured on film only from 900nm to 1,000nm.

**Infrared Energy Rejection (IRER)- The percent of solar infrared energy rejection over the wavelength range from 780-2,500 nm.